



# Hybrid Composite Laminates for Prosthetic Sockets: A Review of Material Selection, Manufacturing Techniques, and Mechanical Performance

Rand Ayad\*

Mechanical Department, College of Engineering, University of Wasit, Wasit, Iraq.

## \*Corresponding Author

Rand Ayad

Mechanical Department,  
College of Engineering,  
University of Wasit, Wasit,  
Iraq.

## Article History

Received: 10.09.2025  
Accepted: 28.11.2025  
Published: 13.01.2026

**Abstract:** One of the most innovative variants of the solution to the field of prosthetic sockets development is hybrid composite laminates that provides a higher level of mechanical efficiency, comfort during usage, and the sustainability of materials. This literature survey addresses how varying types of fibers, including glass, carbon, aramid and natural fibers (like flax) can be incorporated into polymer matrices in a strategic approach to satisfy the multifaceted requirements of a prosthetic. The different types of fibers offer individual mechanical advantages of tensile strength, impact resistance, fatigue resistance and lightweight structure, and this aspect makes the hybrid laminates an alternative to solid materials. The paper explains the role of the choice of the matrix, thermoplastics, thermoset and bio-based resins and the effect they have on the performance of the composite, biocompatibility, and cost. Structural integrity and flexibility of design is further improved by manufacturing techniques such as alternative advanced layering sequences, vacuum-assisted curing, additive manufacturing processes, and so on. Mechanical testing, ISO compliance tests are aspects of quality control that guarantee uniformity in the levels of production. The hybrid laminates can be used in the place of the traditional prosthetic materials, where tensile strength, fatigue, affects absorption are the major aspects, after which they can be designed to fit the individual anatomy by way of being custom-designed. The review indicates both the improvement in mechanical performance, as well as end-user responses, as a larger number of amputees stated that it provided better comfort, reduced weight, and enhanced effects of the functionality. The current research prospects underline the combination of smart materials, environmentally friendly composites, as well as AI-based design optimization. With the changing status of manufacturing technology, the hybrid composite laminates will become available and offer high quality and affordable prosthetic solutions to the world population. This critical review is the basic source of reference to those researchers, clinicians, and engineers working to create the second generation of prosthetic design.1 Hybrid Composite Laminate Introduction to Prosthetics.

**Keywords:** Hybrid Composite Laminates, Prosthetic Socket Design, Fiber-Reinforced Polymers, Additive Manufacturing, Mechanical Performance.

## Cite this article:

Ayad, R., (2026). Hybrid Composite Laminates for Prosthetic Sockets: A Review of Material Selection, Manufacturing Techniques, and Mechanical Performance. *ISAR Journal of Science and Technology*, 4(1), 42-52.



# 1. Introduction

## 1.1. Definition and Overview of Hybrid Composite Laminates

The laminates in a polymer are combined in a hybrid format where two or more classes of fibers come together to provide an excellent mechanical performance. These laminates increase such properties as tensile strength, impact resistance and durability; these properties are needed by the prosthetic applications by combining fibres, such as glass, carbon and aramid. These properties are fine-tuned (via careful layering) during manufacture, and this is done, again, with the weight kept as low as possible, important to the mobility of the user.

Hybrid composites have a solution to the dilemma of finding materials that can withstand mechanical forces but are inexpensive in the application of prosthetics. This will provide designers with greater flexibility in customization of the prosthetic units, doing so in order to suit the requirements of the user. This flexibility is particularly useful due to the creation of a considerable variety of tastes towards comfort and functionality among users.

In this regard, the lap material used affects the overall performance of the laminate; thermoplastics or epoxies are famous due to their mechanical strength and the ability to mix with the body. Selecting the appropriate matrix leads to the process of striking a balance between the flexibility and robustness, as mentioned above. The development of sustainable materials also creates the possibility to have more green solutions that do not spoil the environment but remain on high-performing levels.

Outside their physical capabilities, the hybrid laminates are leading to the advancement of enhanced manufacturing processes. Such processes as automated fiber placement enhance the reliability and acceleration in the process of production, which was discussed previously. The progress in these has demonstrated an apparent attempt to increase the quality standards and reduce the cost-benefit to the producer and the wearer.

In addition, the feedbacks of the users always indicate more comfort and less difficulty in adapting to these new materials than the traditional ones. The use of hybrid composite to make the prosthetic also helps to better the toughness of the prosthetic as well as satisfy their clients by providing them with a one-on-one solution based on their functional needs, (Sam L. Phillips & William Craelius, 2005)[1], (Mashi, 2025)[2] and (Mohan Kumar T S, 2025)[3].

## 1.2. Importance in Prosthetic Applications

By using such materials, such as glass, carbon and aramid fibers, hybrid composite laminates have improved prosthetic with such materials. The composites have the best weight-to-strength ratios and at the same time, they are flexible and durable. This balance is essential in the availability of prosthetics with the reduction in weight not implying compromising structural integrity. Glass fibers offer a cost-effective development in strength and carbon fibers offer high-performance capability to high usage applications.

The flexibility of the hybrid laminates makes them stand out. Fiber layers and orientations are designed and customized to suit needs that are provided by manufacturers. Varying the fiber directions creates optimization of the loads and minimization of weight, which maximizes comfort and mobility. There are also

better ways of curing that enhance the bonding between the layers making the laminate to endure the daily use.

Hybrid composites have higher resistance to fatigue than single-fiber-based materials and prolong the life of the prosthetic limbs with repeated load. The users resulting in higher standards of satisfaction and broad acceptance enjoy the increased comfort and flexibility of the traditional parts.

The prospective innovations involve intelligent, dynamic material in composite hybrid and this offers customized mobility solutions. On the whole, hybrid laminates enhance the work of prosthetics, comfort, and durability at the same time, (Castro-Franco et al., 2025)[4] and (Kebede & Gutata, 2024)[5].

## 1.3. Scope of the Document

This report discusses composite laminates that are hybrids and their effect on the prosthetic sockets. It shows how the choice of various types of fiber such as glass, carbon, and aramid will enhance durability, comfortability and performance. All types of fibers have their mechanical benefits contributing to the effective use of prosthetics.

Special attention is paid to the manufacturing processes, in particular to such processes as layering and curing that guarantee the structural integrity and quality. During the production, quality control is a very critical aspect in ensuring the strength of the composite.

Tensile strength, impact resistance and fatigue performance are among the important mechanical characteristics that are assessed in the paper. These analyses demonstrate hybrid composites are superior to conventional materials by a number of dimensions.

Comparison of hybrid composites vis-a-vis conventional material brings out an advantage and disadvantage to the composites. Analysis includes cost-effectiveness, and it has user feedback on performance difference.

Finally yet importantly, the source focuses on the recent developments in composite materials and methods of their production encouraging possible trends in designing prosthetics in the future. In general, it contains useful insights into the application of hybrid composites in prosthetics and advises the future research to increase comfort and functionality, (Rijwani et al., 2025)[6] and (Nagarajan et al., 2024)[7].

# 2. Material Selection for Prosthetic Sockets

## 2.1. Types of Fibers Used

Prosthetics laminates with fibers that have diverse strengths are present as hybrids. Glass fibers have a high combination of cost, stiffness and strength. Their great tensile and flexural characteristics enable them to be strong and resistant to pressure and impact resistance is their characteristics to support high-force mechanism.

Carbon fibers have an excellent strength to weight ratio and elastic modulus. They also assist the artificial feet in simulating the energy storage and release of natural limbs enhancing movement. The carbon composites are also easier to fatigue than the normal materials thus increasing the life of the prosthetic.

Fibers such as Kevlar which are made of Aramid are tough and

resistance to abrasion. They do not occur much, but provide beneficial impact resistance and durability. These fibers aid in formation of lighter though strong components that deal with the daily dynamic forces.

Hybrid laminates with a mixture of glass, carbon, and aramid are a combination of their most favorable characteristics. Glass gives tensile strength, and is resistant to corrosion. Stiffness and strength is added by carbon. Aramid enhances the impact absorption and strength. These fibers are used together to form strong, flexible prosthetics that would suit the diverse needs of the users, (salman & Kahtan, 2025)[8], (Oleiwi et al., 2022)[9] and (Hussein Kommur Dalfi, 2023)[10].

**2.2. Matrix Materials Considerations**

The selection of correct matrix materials used in hybrid composite laminates in prosthetics has a lot of influence on the strength, the longevity and biocompatibility of the laminates. Discussors usually have the choice of thermoplastics, thermosetting resins, and bio-based. Polyamide and polypropylene are thermoplastics that provide easy processing capability, and are recyclable, flexible, and impact resistant that assist the prosthetics to overcome the daily stresses. An example of thermosetting resin as if epoxy is very strong mechanically and heat stable, leading to higher tensile strength and minimizing deformation. Nonetheless, even homogenizing the epoxy in the process of 3D printing can prove difficult and potentially damage the results.

Natural fibers epoxy resins to produce bio based composites can be regarded as a viable option as a more sustainable alternative due to environmental reduction and biodegradability. However, they have poor fiber-matrix bonding and are vulnerable to moisture making them weak in terms of strength and reliability. Material science

(such as fiber surface treatments and coupling agents) has been able to enhance these bonds. Multiple types of matrices in a single implant are currently being used in some prosthetics to create variable levels of stiffness of the prosthetic to match mechanical requirements of different parts of the body.

The cost-saving performance is also a requisite. Superior composites work well and are costly making them inapplicable in certain health institutions. The advanced prosthetics are affordable and accessible because they are selected carefully, (Mashi, 2025)[2], (Borthakur, 2025)[11] and (Zheng et al., 2025)[12].




Figure 1: Fused Deposition Modeling (FDM) Principle, (Said et al., 2025)[13].

Table 1: Matrix material for 3D-printed CFRPs, (Zheng et al., 2025) [12].

Matrix Material	Type	Characteristics	Application Fields
PLA	Thermoplastic	Low cost, Easy, Biodegradability. sharpening; Reduced mechanical and thermal stability (softens at 50–60 °C)	Medical: Biomedical novice projects. applications
PA6		Superior mechanical characteristics, High-temperature stability	Aerospace, Automotive industry
PEEK		High temperature of continuous services (250 °C), Excellent chemical stability, Maximum mechanical performance.	Aerospace, Automobile industry, Extreme conditions.
ABS		Good impact resistance, good electric insulating qualities, Expatriate chemical stability.	Functional Prototyping, Electrical Engineering.
Epoxy resin	Thermosetting	Excellent High insulation properties. Mechanical performance, High moisture resistance; Complicated treatment, Efforts to be relatively low flame resistant.	Areas Aerospace, Automotive industry, Electronics and electrical engineering.
Phenolic resin		Higher temperature resistance, Better chemical resistance, Small time of curing: Higher absorption of water, Less toughness.	Fire-resistant materials, Acid and alkali-resistant chemical equipment

### 2.3. Criteria for Material Selection

The choice of materials to be used in hybrid composite laminates in prosthetic constructions is a matter of balancing various factors with a high level of consideration in order to have good balance of functionality, comfort and longevity. Such mechanical characteristics as strength, stiffness, resistance to fatigue are now in the limelight. The materials should be able to support when subjected to continuous stress but they must also provide the required support to the users.

Also important in heat management is the management. The materials should assist in dissipating heat at the attachment point between the prosthetic and the residuum to prevent pain or skin issues including sores and excessive sweating. Maintaining the weight level is also important, as lightened parts are easier to move and cause less fatigue during the prolonged usage.

The cost factor is a relevant aspect of the selection of materials at all times. Price can make or break a material to make it considerate in a broad market or merely a niche. Indicatively, carbon fiber fitted polymer (CFRP) boasts of high strength in comparison to its weight; however, it is quite costly. At the same time, the alternatives such as polypropylene or high-density polyethylene (HDPE) are not that efficient as CFRP, but cost-effective.

It is also important in terms of manufacturing. The materials must be compatible with the existing fabrication technologies and enable manufacturers to produce materials of standard quality. Multi-criteria decision-making tools can come in handy in order to work through these complicated trade-offs. They assist the stakeholders to consider the entire situation concurrently and choose some materials, which would best fit the specific considerations of each prosthetic, (Rijwani et al., 2025)[6].




Figure 2: a. computerized model of a stump that has been created through a CT scan of an amputated person. b. Computerized representation of a transtibial-designed prosthetic limb parts, prosthetic socket, liner, suspension system, pylon, and prosthetic foot, (Rijwani et al., 2025)[6].

## 3. Manufacturing Techniques for Hybrid Composite Laminates

### 3.1. Layering Techniques

The process of hybrid composite laminates also has an important role to play in the stability and strength of Prostheses; this is due to the method of layering. This is done by putting in place various materials such as glass, carbon, and aramid fiber in a subtle assembly with a polymer matrix to create a composite that enjoys the property of each of the materials.

There are various methods of layering used by manufacturers, including the old-fashioned and hand-lay to the advanced automated fiber placing. In hand lay-up, the material to be used is laid down on molds by hand until the thickness and orientation is achieved. It is flexible concerning design, time consuming and subject to errors. Conversely, automated fiber placement involves the use of robots to lay fibers onto the surface of a design whereby the control is done to the exact specifications which enhances uniformity and load balance.

Vacuum bagging is a technique used to roll the layers to a compact size with the vacuum applied pressure eliminating the trapped air during the curing process. This works to increase the integrity of the bond between layers and eliminates defects including voids or delamination that can disrupt the laminate. Another alternative is compression molding, but this has to be successful only in case even pressure is exerted on all layers during the curing process.

The mechanical properties such as tensile strength and impact resistance depend on the sequence of arrangement of the layers. It has been found out that the alternation of fiber directions in the stack can increase the load capacity at low weight. In addition, the use of the finite element analysis allows the designer to experiment with various layering patterns in video form prior to the actual production hence a more accurate forecast of the performance.

To sum it up, smart layering strategies are significant in enhancing the effects and longevity of hybrid composite laminates in the context of prosthesis use through the personalization of material behavior by strategically designing composite plans, (Kebede & Gutata, 2024)[5], (Hussein Kommur Dalfi, 2023)[10] and (Fangueiro et al., 2006)[14].

### 3.2. Curing Processes

The process of curing is something that is critical in the development of the hybrid composite laminates and particularly in the manner in which they are used in the creation of the prosthetic devices. This process solidifies the matrix material to fix in the mechanical strength and the overall quality that the final product requires. Thermosetting is one of the common methods of curing, one of the other methods is thermoplastic, and there are more modern methods, such as vacuum bagging and autoclave curing. In resin, thermosetting resin requires heat to initiate a chemical reaction that hardens the composite, whereas thermoplastics can be remodeled and reinvented on several occasions.

Even heat distribution during the curing process is the determinant in prevention of such problems as airpores in the material or inability to thoroughly saturate the fibers with a matrix. Vacuum bagging contributes to the problem by removing the entrained air and bringing the layers close to one another that enhances the

wetting of fibers, smoothness of surfaces, as well as dimensional accuracy. The whole cycle of curing the speed of temperature increase, the duration of constant temperature and the cooling down may the difference between the properties of the laminate. As an illustration, an increase in temperature may enhance strength but would cause warping unless it is done with careful consideration. Such techniques like resin transfer molding (RTM) provide the opportunity to obtain control over heat and pressure in the process of curing.

The producers of the products of the hybrid composite laminates can be able to optimize their processes to ensure that the hybrid composite laminates in the production of prosthetics yield the optimal outcomes. With the progress of the field, effective monitoring during the curing may be employed in real time and may bring the standards in consistency and quality of the product even higher, (Nagarajan et al., 2024, pp. 1-5)[7], (Zheng et al., 2025)[12], (Fangueiro et al., 2006)[14] and (Lee & Chang, 2024)[15].

### 3.3. Quality Control Measures in Manufacturing

The quality control in making the hybrid composite laminate on the manufacturing of prosthetics is critical because of the uniformity in performance and the confidence of the users. These materials undergo many mechanical strains and therefore, consistent quality during manufacturing is necessary. Manufacturers employ different methods to test the composites in each of the production phases.

The part of mechanical testing is significant as it determines tensile strength, fatigue resistance and impact toughness. Such tests make sure that the material does not give in under Day to Day servicing and offers the needed support. As an illustration, tensile strength is essential in the issue of sound functioning of the prosthetics under loading. Periodic review of industry Audits highlight the problems beforehand.

Inspections on raw material are also relevant. Fibers and components of the matrix are evaluated before they are assembled to ensure they are as per specification. The selection of matrices should be of good durability and biocompatibility when it comes to final quality. Follow-ups in the layering process will assist in the detection of flaws such as bad bonding or sealed up voids that might cause the structure to be weak.

The other important aspect is that the curing process needs to be controlled. Regulations of the constant temperature and humidity help preserve flaws, which lead to loss of durability and strength. These conditions are automated and can be adjusted when necessary.

It helps to ensure quality by following the ISO standards and other related provisions. These regulations also govern all its steps such as selecting materials, production and the audits and certification encourage continual improvement and safety on the devices, (Salman & Kahtan, 2025)[8] and (Said et al., 2025)[13].

## 4. Mechanical Performance of Hybrid Composite Laminates

### 4.1. Tensile Strength Characteristics

The tensile strength of hybrid composite laminates is very high and this is essential in the usage of prosthetics. Manufacturers have gained a lot of mechanical performance by using natural fibers in

the form of flax with other synthetic fibers like glass and carbon. Such hybrid materials tend to be superior to traditional materials of the prosthetics due to the perfect combination of fibers and resin matrices.

Research indicates that hybrid composite laminates such as flax-glass-epoxy have tensile strengths that exceed the ones of single-fiber composite. Even distribution of fibers also enhances distribution of the load and the elasticity of the load in the movement during the functioning of a prosthetic. As an illustration, the use of flax fibres between the layers with the decades of glass or carbon on the surface can provide significant contributions to tensile strength and the flexibility of the material.

Because of mechanical tests, tensile strength is found to be much influenced by the manner in which fibers are stacked and oriented. Laminates that have uniformly spaced layers tend to have higher tensile modulus, or improved stiffness bodies as well as strength. Computer models on the approach of finite element analysis show that the hybrid designs are reliable in relation to experimental results.

Furthermore, new techniques of fabrication such as vacuum-assisted resin infusion make certain that the fibers are distributed well in the laminate. This consistency is important in enhancing tensile performance. Ultimately, hybrid composite laminates are also transforming the game as they come up with lightweight but tough prosthetics that will survive day-to-day hardships, (Sam L. Phillips & William Craelius, 2005)[1], (Castro-Franco et al., 2025)[4], (Hussein Kommur Dalfi, 2023)[10] and (Shabeed et al., 2024)[16].

### 4.2. Impact Resistance Analysis

The measurement of impact resistance on hybrid composite laminates is a factor that is vital to consider in the case of prosthetics whereby toughness and safety are paramount. A mixture of fibers such as carbon, glass, aramid and basalt enhances better energy absorption as opposed to normal materials. It is significant to mention that carbon fibers in combination with basalt improve the level of impact protection. The various fiber properties are used to address the needs of the prosthetic.

Research has found out that fiber hybridization enhances the ballistic strength of fiber metal laminates. The enhancement of basalt composition also enhances resistance to high impact blows and retains shape. Layers that are stacked together carefully evenly distribute stress that improves performance.

The finite element analysis is a method employed by engineers to model fiber configurations and optimize the energy detection by eliminating the need of additional weight that is critical in the comfort sense. The alternation of fibers also enhances tensile and influence strength.

Impact tests demonstrate that the damage and recovery of hybrid composites are less as compared to that of a single-fiber composite. This advantage is attributable to the high rates of bonding between fibers and the matrix to pass loads in case of impacts.

Further processing techniques such as vacuum-assisted infusion of resin enhances bonding thus more resistant laminates that do not easily crack. Strength can be enhanced by incorporation of thermoplastic fillers that enhance fracture toughness by more than 27. Practical experience supports the idea that hybrid prosthetics

are more comfortable and voice more resistant and offer safer and longer term devices, (Sam L. Phillips & William Craelius, 2005)[1], (Sun et al., 2025)[17] and (Shabeed et al., 2024)[18].

### 4.3. Fatigue Performance Studies

The situation with fatigue performance in hybrid composite laminates is that without studying fatigue performance in these laminates, we will not be able to know how long lasting these laminates are in terms of reliability in the prosthetic devices. Such materials have to undergo repetitive stresses as prosthetics are subjected to daily patient use hence knowing the response of such materials to cyclic loading can be used to establish their usability. Studies indicate that blends of natural and synthetic fiber become stronger than traditional materials concerning the fatigue strength. An example of this is the use of flax and glass fiber in creating laminates, which have passed the multiple test of loading and loading without breaking.

Testing is generally done to fail the laminates under controlled cyclic forces and investigates the number of cycles the laminates survive, the cracks formed, and their properties. The findings have shown that increasing the fibre volume and layering arrangement both enhance fatigue life. The interaction of the various fibers is also a factor of concern- natural fibers maintain the absorption of energy and synthetic ones give the reinforcement of the tensile strength.

Engineers usually resort to finite element analysis, which is a simulation of the behavior of the hybrids during repeated stresses, to predict the duration of the life of the hybrids in different conditions. Hybrids have been found to be more endurable when the gait cycles resemble actual motions and as a result, the models are designed with customized compositions. These findings suggest that hybrid composites are likely to be sources of promising materials that can be used to integrate comfort and performance with increased fatigue properties in the process of designing prosthesis, (Castro-Franco et al., 2025)[4], (Oleiwi et al., 2022)[9] and (Faheed et al., 2025)[19].

## 5. Comparative Analysis of Hybrid Composites vs. Traditional Materials

### 5.1. Strengths and Weaknesses Comparison

High strength to mass ratios have been provided with hybrid composite laminates in the field of prosthetics as the laminates are color-coded with high-performing and expensive fiber such as carbon and aramid with cheap glass fibers. This combination enhances tensile strength and impact resistance that make the prosthetic devices to be more durable. Leveraging using the method of layering like vacuum bagging improves bonding and minimizes flaws, which creates laminates less affected by stresses and multiple loads. These improvements are aided in the finiteness of the element analysis in forecasting the load-bearing capacity.

It has been reported by the users that hybrid composites are actually much easier to use and less weighty compared to the traditional metal and plastic prosthetic. They also withstand repeated stress very well which is an asset to normal everyday use. The price of raw materials to hybrid laminates is however expensive which may restrict access to some patients or providers. Although hybrids tend to do better under strength, there are cases when a design fails under extreme stress, and the conventional design will perform better.

Research on biocompatibility requires more investigation because the interaction of biocompatibility with body tissues over a long period is unclear. There is also the need in manufacturing new skills and methods which would slow down initial adoption of hybrid composites, (Sam L. Phillips & William Craelius, 2005)[1] and (Hussein Kommur Dalfi, 2023)[10].

### 5.2. Cost-Effectiveness Analysis

Although hybrid composite laminates produced by polyethylene terephthalate (PET) are not entirely free and still cost more than fully carbon fiber, this change is a significant advance to the use of prosthetic sockets in low- and middle-income countries (LMICs). Most of these traditional socket materials such as glass-fiber-reinforced composite (GFRP) and standard thermoplastics such as polypropylene (PP) and high-density polyethylene (HDPE usually have high prices. However, PETr-fiber-reinforced composites provide similar or even higher mechanical properties at a significantly low cost.

The PET composite materials are relatively cheap and easy to produce with comparatively low equipment that makes them suitable in resource-constrained regions where use in prosthetics is concerned. The price of PET fabrics is similar to that of GFRP and other popular materials in LMIC, but much less expensive than carbon fiber that may range between 137 and 174 per meter. PET selection by manufacturers ensures that companies reduce their costs with the equivalent performance of their products.

PET laminates that are tested are tough and strong enough to withstand the forces that the prosthetics need to endure. These attributes show that PET sockets must have the capacity to sustain or beyond the load bearing requirement of daily use. This durability coupled with the cost savings will be beneficial to both the patient and the healthcare giver since the number of replacements that would be done on them reduced and the comfort of the user increased.

PET composite also promotes sustainable restoration beyond immediate monetary benefits since it could be locally produced. This does not only aid in satisfying the current urgent need to have cheap prosthetics but also provides employment, assisting the society that is directly affected by lack of accessibility of quality health provision, (Nagarajan et al., 2024)[7] and (Nagarajan et al., 2023)[20].

Table 2: The dominant mechanical and physical characteristics of the sockets to be evaluated, (Nagarajan et al., 2023)[20].

Socket	Wall Thickness at Distal End (mm)	Stiffness (N/mm)	Displacement at 1250 N (mm)	Socket Weight (g)	Specific Stiffness (N/mm <sup>2</sup> )/mmg	Cost \$/kg
GFRP	4.41 ± 0.2	319 ± 3	4.77 ± 0.06	595	0.5361	15–54
PETW	5.80 ± 0.1	233 ± 2	5.37 ± 0.23	297	0.7845	13
PETK	5.50 ± 0.1	159 ± 5	7.16 ± 0.12	245	0.6490	13
HDPE	5.10 ± 0.4	140 ± 2	9.54 ± 0.80	283	0.4947	4–15
PP	6.60 ± 0.3	135 ± 1	10.91 ± 0.10	261	0.5172	20–86

### 5.3. User Feedback on Performance Differences

There have been positive reports by users concerning hybrid composite laminates in prosthetics, in which there is evident advantages over the conventional materials. Hybrid sockets such as polyethylene terephthalate (PET) and dual polymer combos are also found to fit the residual limb better, which relieves stress on the skin and pressure that lead to discomfort with older materials.

The other benefit that is cited by the users is the light feel of these composites when compared with the fiberglass or the usual thermoplastics. This decreased weight enables the wearers to move more easily and have fewer fatigues during the day. It is also the fact that people compliment these materials on their high tensile strength levels and impact resistance rates whereby the sockets will work well with the various stress levels. Active lifestyle with or without injury is also a crucial factor that makes PET-fiber-reinforced sockets important to those who require it endure frequent usage without becoming deformed and unusable.

It is also a significant consideration in cost. The users who live in lower-income areas have mentioned that compared to it, hybrid composites are less expensive and readily available than the traditional forms of prosthetics. Research has also discovered that there is a difference in overall satisfaction with the overall socket performance based on the material used to make the sockets; be it it is a woven or knitted.

It is worth noting that these hybrid sockets were initially associated with challenges by some users as they were used to these sockets. They required some modifications to fit into their support and get the right fit. Nevertheless, it is unanimously agreed that hybrid composite laminates have enormous potential that can ensure much more comfort and durability to the prosthetics and eventually result in the better lives of amputees, (Nagarajan et al., 2024)[7] and (Nagarajan et al., 2023)[20].

## 6. Future Trends in Hybrid Composite Materials for Prosthetics

### 6.1. Innovations in Material Science

Hybrid composite laminates of prosthetics are changing because of recent developments in materials science. Continuous fiber-reinforced polymers (CFRPs) are both strong and flexible as well

as lightweight, improves product durability, and allows complex forms. The additive manufacturing process with specific attention to fused deposition modeling (FDM) creates elaborate intended structures with continuous carbon fibers, which enhances the mechanical performance.

Smart materials changing with the environment also come under the scrutiny of researchers. None of the androids feels at ease using a bone-integrating and comfortable bioactive alloy like the shape memory ones. Bioactive and antimicrobial-containing new composites enhance the control of infection and infection prevention in prosthetics, thereby enhancing the safety of the product.

These materials are further improved by Nanotechnology. The incorporation of nanoparticles enhances the strength, lowers weight and body compatibility. Self-healing polymers are expected to be promising because minor deformities will auto-repair on the polymer, prolonging the life of the prosthetic, exempting the prosthetics of frequent repairs.

The sustainability under consideration is acquired due to the natural-synthetic fiber blends, such as flax-glass laminates. These hybrids have high mechanical characteristics, and have a lesser impact on the environment. Initial results indicate that eco-friendly composites are structurally stable and may become widely used in terms of more ecological versions of prostheses, (Zheng et al., 2025)[12], (Borthakur, 2025)[11], (Castro-Franco et al., 2025)[4], (Mashi, 2025)[2] and (Maqsood et al., 2024)[21].

### 6.2. Advances in Manufacturing Technologies

The additive manufacturing advancement has helped in the development of manufacturing technologies of the hybrid composite laminates utilized in the manufacturing of prostheses. The development of multi-material additive methods is notable, because it allows it to print complex shapes and tailored material behavior in a single additive process. The style combines different resources in a very smooth manner that enhances functionality and performance. To illustrate, ceramics made of polymer are leading the pack with unique properties that are applicable in certain prosthetics requirements.

Similarly, research has also been making progress in terms of continuous carbon fiber-reinforced polymer using material

extrusion technology such as fused deposition modeling (FDM). This is not only useful in enhancing mechanical properties, but also in improving complex designs that are very difficult to achieve through the traditional methods. Prior impregnation of the fibers prior to extrusion has been useful in setting the performance bar higher such that composites can withstand the challenge of tough prostheses.

Smart materials keep resonating with the boundaries by changing with environmental modifications and demands of the users. Their flexibility represents long-lasting and under-serviced prosthetics. Scientists are also striving to include the biocompatible materials

that enhance closer access to the body that will enhance the comfortability of the wearers and their general experience with it.

To this, artificial intelligence and machine learning are moving into the limelight to perfect AM processes. These technologies are able to filter through the information and identify trends so that material blends and processing steps are streamlined. It results in a significant improvement of quality, efficiency, and saving of waste, which provides the manufacture of prosthetic with a keen edge, (Mashi, 2025)[2], (Said et al., 2025)[13], (Maqsood et al., 2024)[21] and (Nazir et al., 2023)[22].

Table 3: Selection of materials to be used by some AM methods in terms of mechanical requirement, (Said et al., 2025)[13].

Requirement	Description	Recommendation
<b>Tensile strength</b>	The tensile stresses on the material to resist fracture are important. The printable material considered in this instance is supposed to have high tensile strength that is important in components that carry loads, are used structurally or in both mechanical and statical applications.	FDM: PLA SLS: Nylon 12, Nylon composites SLA: lifting tool, solid curved plastic kit, Rigid Resin, Alumina 4N Resin.
<b>Flexural modulus</b>	Flexibility is the capacity of a material to counter deformation in response to a strain. It is a good way of determining the stiffness (high modulus) or flexibility (low modulus) of the material. The elements that are being used in print should be capable of flexure and tensile resistance.	FDM: ABS (medium), PLA (high). SLA: Flexible and Elastic Resins (low), Tough and Durable Resin (medium) Rigid Resin (high). SLS: Nylon 12 (med.), Nylon composites (high).
<b>Elongation</b>	Stress strain resistance of a material at elongation. It enables one to compare materials according to their stretchability and determine whether a material will be deformed before it breaks or it fails suddenly. Elasticity of printed parts should be to be tough and durable.	FDM: ABS (medium), TPU (high) SLS: nylon 12 (med), nylon 11(med), polypropylene (med), TPU (high). SLA, Tough and Dure Resins (mediums), Polyurethane Resins (mediums), Flexible and Elastic Resins (highs) and Silicone 40A Resin (highs).
<b>Impact strength</b>	The capacity of a substance to receive the shock and impact energy without fracture. This is a property that is tough and durable and assistance to conclude the likelihood of the material breaking once dropped or hitting another object. The printed objects are normally in application in conditions of some impact.	FDM: ABS, Nylon SLA: Tough 2000 resin, tough 1500 resin, Grey pro resin, durable resin, polyurethane resins. SLS: polypropylene, nylon composites, nylon 12, nylon 11.
<b>Hardness</b>	The performance of materials when put on the surface level. This also assists in deciding how soft plastics like rubber and elastomers should be to a certain degree based on the application. In this case with the printed products being the rubber materials, there is a preference on flexible materials.	FDM: TPU SLA: Flexible Resin, Elastic Resin, Silicone 40A Resin SLS: TPU
<b>Tear strength</b>	Tensile strength of material to swelling of cuts. This property is a necessity when measuring the wear life and strength against tearing of soft plastics and other flexible substances like rubber. Printed products based on flexible resin or TPU present this strength and durability.	FDM: TPU SLA: Flexible Resin, Elastic Resin, Silicone 40A Resin SLS: TPU

Requirement	Description	Recommendation
<b>Compression set</b>	Permanent deformation following compression is used to determine whether material is going to revert to its original shape when the exerted force is withdrawn. This property is important in applications involving soft plastics and elasticity and it makes the material retain its shape with time. Which is also standard with prints with a flexible resin and TPU.	FDM: TPU SLA: Flexible Resin, Elastic Resin, Silicone Resin 40A. SLS: TPU
<b>Heat deflection temperature</b>	This is the temperature at which a certain material will deform under a specified load. This measurement can be used to know whether a material is suitable to be used in areas where there is high temperature or not. Nylon samples in print form would be resistant to various loads at high temperatures.	High Temp Resin, Rigid resin, 4N Alumina resin. SLS: nylon 12, nylon 11, nylon composites.
<b>Creep</b>	Creep is the ability of a material to experience permanent deformation when it is exposed to long-term stress loads of tensile, compressive, shear or bending forces. Hard plastics with low creep are preferable in the construction of structures in which high stability and durability are required. Which is characteristic of prints that are of polyurethane or nylon.	FDM: ABS Polyurethane Resins, Rigid Resins, Alumina 4N Resin, SLA. SLS: nylon 12, nylon 11, nylon composites, polypropylene.

### 6.3. Potential Market Growth Areas

Development of materials and technology has provided the market with a promising future of hybrid composite laminates in making prosthesis. The development of 3D printing is one of them since it allows the creation of a prosthetic specially designed to meet a particular patient. The strength of the device is enhanced by using of advanced materials like carbon fiber-reinforced polymer and biocompatible alloys that reduce the weight of the prosthesis that is a major disadvantage of traditional prosthetics. In the meantime, with the maturation of bio printing, we realize new possibilities to fabricate components that are better replications of human tissue to increase comfort and functionality.

The demand of the tailored-made prosthetic devices is steadily increasing too, as patients are now more concerned with patient-centered care. Advanced design software and simulation tools assist the experts in developing distinct forms that have a balance between aesthetics and mechanical effectiveness. To top it all increasing sustainability issues in healthcare open up the entrance of the green composite materials that are effective and reduce environmental footprints.

The Orthopedics provides additional opportunities to develop because of the usage of hybrid composites in bone replacement and support systems with the help of their lightness and durability. This might accelerate curing and give better patient results in general. With the continuous development of technology, intelligent materials that can monitor health or react to its environment are sure to make user experiences even more colorful and expand opportunities in the market even further, (Borthakur, 2025)[11], (Zheng et al., 2025)[12] and (Said et al., 2025)[13].

## 7. Conclusion and Recommendation

### 7.1. Summary of Key Findings

By mixing both natural and composite fibers such as flax, glass, carbon and aramid, hybrid composite laminates are promising to be very successful in prostheses. The glass fibers are more durable and cheaper, whereas the carbon fibers are better in terms of

strength to weight ratios being used in high performance. Aramids enhance toughness and influence strength that enhances durability.

The strength and body compatibility of the device depends on the choice of the matrix materials, like the thermoplastics, or epoxy resins. The selection of the materials is based on the mechanical strength, prices and production processes.

The production of laminates is improved due to manufacturing progress. Layering methods expand the design capacity whereas the curing makes the final product stronger. Quality control is also essential in order to achieve high standards.

Hybrid composites have been tested to be better in tensile strength, impact resistance and fatigue life that are considered traditional materials. These prosthetics are more comfortable and versatile to the users. Nevertheless, such issues as cost and biocompatibility exist.

Development opportunities in material science Future developments in the field of smart materials, additive manufacturing, can offer custom design and functionalities. The business is expanding, fuelled by green compounds and need to have custom prostheses.

In general, hybrid composites have a high level of performance, cost-effectiveness and sustainability to enhance the quality of life of the amputees.

### 7.2. Recommendations for Future Research Directions

The development of hybrid composite laminates to be used in the fabrication of prosthetics needs to be researched into better the performance of their material and the ease of use. Advances in material science have the potential of diversifying the type and quantity of printable materials and biomaterials to increase their strength and biocompatibility. Devices may also be given useful additions by the use of smart material that responds to the needs of the users.

Techniques of manufacturing, particularly addition methods, have to be explored further. The minimization of parameters such as the

curing times and the layers can help to increase the durability and decrease the cost. It is important to have uniformity in production through consistency in quality control.

Sustainability provides an opportunity to develop by introducing elements that are environmentally friendly, including biodegradable resins and natural fabrics, without losing performance. This change is better towards the environmental issues and the duration of device life.

It is important to listen to the feedback of users. The knowledge of difficulty of amputees using existing material will also make future design and usability better. This preoccupation renders the prosthetics to be more precise to the actual requirements.

Lastly, it is hard to scale up on production. Improved partnership between the universities and industry would accelerate the innovation process and aid in the introduction of hybrid composite prosthetics to a broader audience. Such initiatives are bringing about more powerful, intelligent, eco-friendly, and more user-friendly devices, (Rijwani et al., 2025)[6], (Said et al., 2025)[13], (Faheed et al., 2025)[19] and (Nagarajan et al., 2023)[20].

### 7.3. Final Thoughts on Adoption in Prosthetics Industry

Designing of the hybrid composite laminates is quite a progressive step towards designing and performance of the prosthetic devices. Combining natural and synthetic fibers as discussed above has an added advantage since it provides mechanical properties unique to enhance performance besides reducing weight. Such a balance between durability and lightness is very important to the intended users who would want to be practical and comfortable in their daily use.

In addition, studies indicate that such laminates are superior in terms of mechanical strength, more so tensile strength as well as against fatigue. These composites have been found to be better in terms of durability and fitting comfort than the traditional materials, which leaves users to believe that they might be more accepted. User comments support the view that they like the fact that these upgraded prosthetics are more adaptable and give high performance in comparison to the traditional ones.

In the future, it will continue to push the innovations in the area of material science to approach the hybrid composite to the broader practice. Further development is necessary not only to enhance mechanical opportunities, but also to eco-friendly and biocompatible materials. As an instance, the use of bio-based resins, including natural fibers, may be integrated in the company in order to align the manufacturing with environmental objectives, which must also meet user needs.

Modern technology as far as production techniques are concerned is also important. Such techniques as additive manufacturing make it possible to customize prosthetics to fit the anatomy of a particular individual better than a typical approach. It is a customization that is critical in improving fit and functionality that has a direct impact on user satisfaction.

In conclusion, it is imperative to promote a good working relationship between the engineers, material scientists, and the clinicians to promote this field. Collaboration will help to optimize the existing technologies, and spur the development of new solutions to suit a large variety of patients worldwide, (Castro-Franco et al., 2025)[4] and (salman & Kahtan, 2025)[8].

## References

- [1] Sam L. Phillips. CP and William Craelius. PhD. (2005). Material Properties of Selected Prosthetic Laminates. [https://www.researchgate.net/publication/232123005\\_Material\\_Properties\\_of\\_Selected\\_Prosthetic\\_Laminates](https://www.researchgate.net/publication/232123005_Material_Properties_of_Selected_Prosthetic_Laminates)
- [2] Zahraa Kareem Mashi. (2025). From Metals to Composite Materials: A Comprehensive Review of Materials Used in Prosthetic Limb Manufacturing. [https://www.researchgate.net/publication/395128285\\_From\\_Metals\\_to\\_Composite\\_Materials\\_A\\_Comprehensive\\_Review\\_of\\_Materials\\_Used\\_in\\_Prosthetic\\_Limb\\_Manufacturing](https://www.researchgate.net/publication/395128285_From_Metals_to_Composite_Materials_A_Comprehensive_Review_of_Materials_Used_in_Prosthetic_Limb_Manufacturing)
- [3] Mohan Kumar T S,Sharnappa Joladarashi,S M Kulkarni. (2025). Comprehensive review of modeling and material selection for hybrid sandwich composites for ballistic impact application using Six Sigma DMAIC methodology - Mohan Kumar T S, Sharnappa Joladarashi, S M Kulkarni, 2025. <https://journals.sagepub.com/doi/10.1177/09544062251315327>
- [4] Angel D. Castro-Franco, Miriam Siqueiros-Hernández, Virginia García-Angel, Ismael Mendoza-Muñoz, Benjamín González-Vizcarra, Hernán D. Magaña-Almaguer and Lidia E. Vargas-Osuna. (2025). Hybrid Laminates Reinforced with Natural and Synthetic Fibers: Experimental Characterization and Preliminary Finite Element Assessment for Prosthetic Applications. <https://www.mdpi.com/2079-6439/13/8/107>
- [5] Galana Abay Kebede and Gamachis Ragasa Gutata. (2024). Characterizing tensile and flexural properties of synthetic fibers-reinforced epoxy composite for foot prosthetic application. <https://www.sciencedirect.com/science/article/pii/S2405844024145021>
- [6] Tarun Rijwani, Gurusharan Dumra, Kumar Abhishek and Ganesh Iyer. (2025). Hybrid multi-criteria decision making approaches for transtibial prostheses socket material selection. <https://link.springer.com/article/10.1007/s42452-025-06841-5>
- [7] Yogeshvaran R. Nagarajan, Farukh Farukh, Arjan Buis and Karthikeyan Kandan. (2024). Single Polymer Composites: An Innovative Solution for Lower Limb Prosthetic Sockets. <https://strathprints.strath.ac.uk/89006/7/Nagarajan-et-al-Prosthesis-2024-Single-polymer-composites-an-innovative-solution.pdf>
- [8] Asala k. salman and Yassr Y. Kahtan. (2025). Review study: variation of prosthetic feet, materials and production techniques. <https://iasj.rdd.edu.iq/journals/uploads/2025/08/21/81491d37454b31bffc7379373c21c918.pdf>
- [9] Jawad K. Oleiwi, Qahtan A. Hamad and Shereen A. Abdulrahman. (2022). Flexural, impact and max. shear stress properties of fibers composite for prosthetic socket. <https://www.sciencedirect.com/science/article/abs/pii/S2214785321081098>
- [10] Hussein Komur Dalfi,Rand Ayad,Khadhum Shabeeb,Khayale Jan,Roy Conway. (2023). Enhancing the quasi-static strength of prosthetic socket made from composite laminates via hybridisation: Experimental and numerical study - Hussein Komur Dalfi, Rand Ayad, Khadhum Shabeeb, Khayale Jan, Roy Conway, 2023. <https://journals.sagepub.com/doi/abs/10.1177/152808372311>

- [78567](https://www.mdpi.com/2673-4591/81/1/10)
- [11] Partha Protim Borthakur. (2025). The Role and Future Directions of 3D Printing in Custom Prosthetic Design. <https://www.mdpi.com/2673-4591/81/1/10>
- [12] Haoyuan Zheng, Shaowei Zhu, Liming Chen, Lianchao Wang, Hanbo Zhang, Peixu Wang, Kefan Sun, Haorui Wang and Chengtao Liu. (2025). 3D Printing Continuous Fiber Reinforced Polymers: A Review of Material Selection, Process, and Mechanics-Function Integration for Targeted Applications. <https://www.mdpi.com/2073-4360/17/12/1601>
- [13] Lotfi Ben Said, Badreddine Ayadi, Sattam Alharbi and Fakhreddine Dammak. (2025). Machines 2025, 13 (9), 813. <https://www.mdpi.com/2075-1702/13/9/813>
- [14] R Fanguero, R Alagirusamy, V Ogale and N Padaki. (2006). Hybrid Yarns and Textile Preforming for Thermoplastic Composites. <https://www.tandfonline.com/doi/abs/10.1533/tepr.2006.0004>
- [15] Ho-Seok Lee and Seung-Hwan Chang. (2024). Thermoforming of partially biodegradable hybrid thermoplastic composites for bone plate applications. <https://www.sciencedirect.com/science/article/pii/S1359836823006261>
- [16] Shabeed. Khahum, Ayad. Rand and Dalfi. Hussein. (2024). The effect of hybridisation reinforcement on the mechanical and physical properties of under-knee prosthesis sockets made of composite laminates. [https://pubs.aip.org/aip/acp/article-pdf/doi/10.1063/5.0213279/19917034/030002\\_1\\_5.0213279.pdf](https://pubs.aip.org/aip/acp/article-pdf/doi/10.1063/5.0213279/19917034/030002_1_5.0213279.pdf)
- [17] Weifu Sun, Yu Wang and Weifeng Wang. (2025). Ballistic impact response of hybrid carbon/basalt fiber metal laminates under various hybridization and stacking sequences. <https://www.sciencedirect.com/science/article/pii/S1359835X25004336>
- [18] Shabeed. Khahum, Ayad. Rand and Dalfi. Hussein. (2024). Reinforcement effects on the mechanical properties of prosthesis sockets made of composite laminates. [https://pubs.aip.org/aip/acp/article-pdf/doi/10.1063/5.0213278/19917125/030001\\_1\\_5.0213278.pdf](https://pubs.aip.org/aip/acp/article-pdf/doi/10.1063/5.0213278/19917125/030001_1_5.0213278.pdf)
- [19] Noor K. Faheed, Rasha Abdul-Hassan Issa, Qahtan A. Hamad, Maryam J. Jaafar and Mahmood S. Mahmood. (2025). Design and evaluation of a novel bioinspired prosthetic foot for running applications in lower limb amputees. [https://biomat-trans.com/journal/BMT/articles/online\\_first/184](https://biomat-trans.com/journal/BMT/articles/online_first/184)
- [20] Yogeshvaran R. Nagarajan, Farukh, Vadim V. Silberschmidt, Karthikeyan Kandan, Radheshyam Rathore, Amit Kumar Singh and Pooja Mukul. (2023). Strength Assessment of PET Composite Prosthetic Sockets. <https://www.mdpi.com/1996-1944/16/13/4606>
- [21] Nabeel Maqsood, Marius Rimašauskas, Morteza Ghobakhloo, Genrik Mordas and Kateřina Skotnicová. (2024). Additive manufacturing of continuous carbon fiber reinforced polymer composites using materials extrusion process. Mechanical properties, process parameters, fracture analysis, challenges, and future prospect. A review. <https://link.springer.com/article/10.1007/s42114-024-01035-w>
- [22] Aamer Nazir, Ozkan Gokcekaya, Kazi Md Masum Billah, Onur Ertugrul, Jingchao Jiang, Jiayu Sun and Sajjad Hussain. (2023). Multi-material additive manufacturing: A systematic review of design, properties, applications, challenges, and 3D printing of materials and cellular metamaterials. <https://www.sciencedirect.com/science/article/pii/S026412752300076X>